

Accura® Stereolithography (SLA®) Material Selection Guide



	Material Properties/Characteristics						Key Application Areas					
	Accuracy	HiTemp	Moisture Resistance	Optical Clarity	Durability	Color	Investment Casting/ QuickCast	RTV/Master Patterns	Snap Fit Assemblies	General Purpose Models	Automotive-Under the hood	WindTunnel Testing
Polypropylene-Like Class												
Accura 25	●●●●		●●●		●●●●	White		●●●●	●●●●	●●●●		
Accura PP White (SL 7811)	●●●		●●●●		●●●●	White		●●●	●●●●	●●●		
Tough/Durable Class												
Accura Xtreme	●●●●		●●●		●●●●	Grey		●●●●	●●●●	●●●●		
Accura Xtreme White 200	●●●●				●●●●●	White		●●●	●●●●●	●●●		
ABS-Like Class												
Accura 55	●●●●		●●●		●●●	White		●●●	●●●	●●●●		
Accura ABS White (SL 7810)	●●●		●●●●		●●●●	White		●●●	●●●	●●●		
Accura ABS Black (SL 7820)	●●●		●●●●		●●●●	Black		●●●	●●●	●●●		
Clear Class												
Accura ClearVue Free (SL 7870)	●●●		●●●●	●●●●	●●●●	Clear	●●●	●●●	●●●	●●●		
Accura ClearVue	●●●		●●●●●	●●●●●	●●●●	Clear		●●●	●●●	●●●		
Accura 60	●●●●		●●●	●●●	●●●	Clear-bluish	●●●●	●●●●	●●●	●●●●●		
Casting Class												
Accura CastPro	●●●●		●●●●●			Clear Amber	●●●●●					
Accura CastPro Free (SL 7800)			●●●			Clear Amber	●●●●●					
High Temp & Composite Class												
Accura 48 HTR		●●●●	●●●			Clear Amber					●●●●	
Accura SL 5530		●●●●	●●●			Clear Amber					●●●	
Accura PEAK	●●●●	●●●●	●●●●			Translucent Amber					●●●●●	●●●●
Accura CeraMAX	●●●●●	●●●●●	●●●●●			White						●●●●●
Accura Bluestone	●●●●●	●●●●●	●●●●●			Blue						●●●●●

Ranking: A five-star rating is superior—ratings are relative to other materials presented.

RATING SYSTEM



Accura® Stereolithography (SLA®) Material Selection Guide



	Viscosity	Flexural Modulus (MPa)	Flexural Strength (MPa)	Tensile Modulus (MPa)	Tensile Strength (MPa)	Elongation at Break	Impact Strength (J/m)	Heat Defl. Temp
	(@ 30° C)	ASTM D 790	ASTM D 790	ASTM D 638	ASTM D 638	ASTM D 638	ASTM D 256	ASTM D 648
Polypropylene-Like Class								
Accura 25	250	1380-1660	55-58	1590-1660	38	13-20%	19-24	@ 66 PSI - 58-63° C @ 264 PSI - 51-55° C
Accura PP White (SL 7811)	210	1960-2060	64-66	2030-2230	40-42	7-13%	42-59	@ 66 PSI - 47° C
Tough/Durable Class								
Accura Xtreme	250-300	1520-2070	52-71	1790-1980	33-44	14-22%	35-52	@ 66 PSI - 62° C @ 264 PSI - 54° C
Accura Xtreme White 200	650-750	2350-2550	75-79	2300-2630	45-50	7-20%	55-66	@ 66 PSI - 47° C @ 264 PSI - 42° C
ABS-Like Class								
Accura 55	155-185	2690-3240	88-110	3200-3380	63-68	5-8%	12-22	@ 66 PSI - 55-58° C @ 264 PSI - 51-53° C
Accura ABS White (SL 7810)	210	2040-2120	74-76	2290-2400	46-48	8-14%	24-47	@ 66 PSI - 51° C
Accura ABS Black (SL 7820)	210	2260-2370	75-78	1890-2440	45-47	6-13%	39-56	@ 66 PSI - 51° C
Clear Class								
Accura ClearVue Free (SL 7870)	180	1940-2250	73-76	1920-2010	38-42	10-22%	23-51	@ 66 PSI - 48° C @ 264 PSI - 41° C
Accura ClearVue	235-260	1980-2310	72-84	2270-2640	46-53	3-15%	40-58	@ 66 PSI - 51° C @ 264 PSI - 50° C
Accura 60	150-180	2700-3000	87-101	2690-3100	58-68	5-13%	15-25	@ 66 PSI - 53-55° C @ 264 PSI - 48-50° C
CastPRO Class								
Accura CastPro	240-260	2310-2340	82-84	2490-2620	52-53	4.1-8.3%	43-49.5	@ 66 PSI - 51° C @ 264 PSI - 50° C
Accura CastPro Free (SL 7800)	205	2200-2480	81-83	1940-2350	45-48	9-19%	35-50	@ 66 - 62° C
High Temp & Composite Class								
Accura 48 HTR	200-250	2760-3400	105-118	2800-3980	64-67	4-7%	22-29	@ 66 PSI - 65° C @ 264 PSI - 57° C
Accura SL 5530	210-270	2620-3240	63-87	2889-3144	57-61	3.8-4.4%	21	@ 66 PSI - 70-85° C @ 264 PSI - 55-58° C
Accura PEAK	605	4180-4790	77-126	4220-4790	57-78	1.3-2.5%	21.3-27.3	@ 66 PSI - 78° C @ 264 PSI - 59° C
Accura CeraMAX	1500-2000	8270-8370	137-145	9460-9680	78-87	1.0-1.5%	14.5-17.9	@ 66 PSI - 148° C @ 264 PSI - 95° C
Accura Bluestone	1200-1800	8300-9800	124-154	7600-11700	66-68	1.4-2.4%	13-17	@ 66 PSI - 65-66° C @ 264 PSI - 65° C

USA
Tel: +1 803.326.4080
Toll Free: +1 800.889.2964
moreinfo@3dsystems.com

UK
Tel: (+44) 1442 282 600
info@3dsystems-europe.com

**Germany, Scandinavia,
Eastern Europe, Middle East**
Tel: (+49) 6151 357 0
info@3dsystems-europe.com

Asia-Pacific
Melbourne Tel: +61 3 9819 4422
Sydney Tel: +61 2 9516 5571
3dprinters.asiapac@3dsystems.com

© 2013 by 3D Systems Inc. All rights reserved. Specifications subject to change without notice. Accura, SLA, 3D Systems and the 3D Systems logo are registered trademarks of 3D Systems, Inc.